

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2000-100399

(43)Date of publication of application : 07.04.2000

(51)Int.Cl.

H01M 2/08
H01M 2/12
H01M 10/40

(21)Application number : 10-266502

(71)Applicant : TOSHIBA BATTERY CO LTD

(22)Date of filing : 21.09.1998


(72)Inventor : FUJIWARA AIICHIRO

(54) MANUFACTURE OF POLYMER LITHIUM SECONDARY BATTERY

(57)Abstract:

PROBLEM TO BE SOLVED: To improve safety by preventing ruptures upon generation of gases due to overcharge or the like.

SOLUTION: This manufacturing method is for a polymer lithium secondary battery, which has a structure where a generating element 1, is housed in an externally attached film 13 with the open periphery thermally fused, and at least one part of a sealing part functioning as a safety valve. Thermal fusion temperature for a sealing zone 14 which functions as a safety valve is made lower than the thermal fusion temperature for a sealing region having no safety valve function.



LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2000 Japan Patent Office